

Technical Data Sheet

RollAnode

Zinc sacrificial anodes for corrosion control of steel in concrete

Description

These sacrificial zinc anodes are specifically designed for application in pre-drilled holes, concrete rehabilitation, patch repair, or newly casted prefabricated concrete elements, which are embedded in an ion-conductive auto moistening paste, for cathodic protection/prevention of reinforced concrete structures.

Several typical examples of applications:

- In combination with concrete patch repair
- Bridge deck or beam supports and columns
- Zones of newly casted concrete adhere onto an existing structure
- Balcony facings and concrete facades
- Concrete slabs

The **RollAnode** consists of a rolled up zinc-sheet with or without ion-conductive adhesive which during installation will be embedded in an ion-conductive self-moistening paste keeping the anodes active during their entire service-life.

This paste (**ZAP** = Zinc anode Activation Paste) is delivered seperately in 600ml sausages which can be applied with standard manual or battery powered sealant guns.

These anodes are utilized in those areas where high expectancy of corrosion is expected. They guarantee a strong reduction of corrosion and preventing new locations with initiation of corrosion.



Service life and design

The service life of the anodes is directly related to the following variables: total zinc weight per unity surface area, steel surface area (steel density), presence and availability of oxidizing agents (O2, H2O) to maintain the cathodic reactions on the steel structure, and the anode's capacity.

Thanks to the simplicity and quickness of the installation, application costs can be reduced to a minimum.

The eventual driving force between those anodes and the steel reinforcement guarantees a long and corrosion-free service life of the structure.



Possible length	50 -900 mm
Possible diameters	15mm – 50mm
Weight	50 -1500 gr
Stock conditions	< 25°C < 50% RH
Maximum storage time	12months (original packing)
Tarriff nr.	7905 00 00

CP Design

In line with other CP systems, a CP system based on **RollAnodes** should be designed by qualified and certified specialists and installed by qualified and experienced contractors. Refer to the international standard ISO12696 "Cathodic protection of steel in concrete". For further recommendations refer to the General Description and Installation Guidelines.

Any cable connection of the **RollAnodes** should be designed by qualified specialists and can be tailor-made for the client.

Performance characteristics

Depolarization of Reinforcing Steel according to the international standard EN/ISO12696 "Cathodic protection of steel in concrete".

The **RollAnodes** may show some self-corrosion over time by discolouring or white deposit. Because of the purity of the zinc this is completely normal and does not effect the performance.

CorrPRE Engineering BV, Zuidbaan 509, 2841MD Moordrecht, Netherlands

Revision Nr.Revision dateApproved0501 Oktober 2023R. Giorgini

All technical data stated in this Technical Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control. The information, and, in particular, the recommendations relating to the application and end-use of CorrPRE's products, are given in good faith based on CorrPRE's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with CorrPRE's recommendations.